



# Product information | TECHNICAL DATA SHEET

**MAXIMO.** Solid Colors. Gloss paint, high pressure, perfect coverage and fast drying. 750 ml, 20 0z, 568 g

### **GENERAL DESCRIPTION**

With a capacity of 750 ml, this is the ideal product for painting large surfaces quickly and conveniently, with coverage of 4 m2. High quality, quick dry alkyd gloss enamel for a perfect finish with very good colour retention and weather resistance.

### **FEATURES**

- High pressure.
- Very fast drying.
- Excellent flexibility.
- Easy to apply and repaint.
- Good hardening.
- Does not contain lead nor other heavy metals.
- High covering power.
- Very good resistance to the sun and rain.
- Retains its glossiness and color.
- Very good resistance to UV light (see chart).
- Strong resistance to scratching once the film is polymerized.

## INSTRUCTIONS FOR USE

- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. On rusty metallic surfaces remove rust with a wire brush and prepare an anti-rust primer if considered necessary. Apply an anchor layer on plastics and polyesters.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within fifteen minutes with the same paint.
- Turn the aerosol upside down to clean out the valve after use. If te nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

# PHYSICAL PROPERTIES

High pressure:	Polyvalent female valve
Propulseur:	Butane / Propane / Mix
Type of liant:	Modified alkyd
Color:	Black
Dry to the touch (ASTM D-1640 ISO 1517):	15'
Completely dry (ASTM D-1640 ISO 1517):	24 h
Thickness of dry layer (ASTM D-823 ISO 2808 ):	15 micras/layer
Adherence (ASTM D-3359 ISO 2409):	3 B
Theorical yield (continuous painting):	6,8 m <sup>2</sup> for 750 ml
Thinner:	Aromatic mixt
Product life:	(Well Stored) >5 years
Condition for application:	Minimum room temperature 8°C
	Surface temperature 5°C a 50°C
	Max humidity 85% R.H.P
Heat resistance of paint:	100°C
	After 15'

<sup>\*</sup> All of the adherence tests have been carried out on iron plates.

#### **APPLICATIONS**

Owing to the product's characteristics, the recommended use is for retouches and painting on all types of materials, whether for domestic uses, crafts, fine arts, or ultimately for anything which requires the properties found in a high-quality spray paint.

- Graffiti Decoration
- Decoration Fine arts Retouches for metallic components.
- DIY Plastics

### **APPEARANCE**



LABEL CAP SYSTEM











# **CAUTION**















## **PACKAGING**

High pressure.

Nominal capacity: 750 ml.

Heat resistanve of packaging: <50°C

Propellant: GLP - HC C<sub>3</sub>-C<sub>4</sub>

Box (6 units) 200 X 340 X 140 mm.









# Product information | TECHNICAL DATA SHEET

**MAXIMO.** Metallic color. Gloss paint, high pressure, perfect coverage and fast drying. 400 ml, 20 0z, 568 g

### **GENERAL DESCRIPTION**

With a capacity of 750 ml, this is the ideal product for painting large surfaces quickly and conveniently, with coverage of 4  $m^2$ .

Acrylic gloss enamel formulated with very high quality resins and leafing aluminium. With a very fast drying action, it leverages the power of the valve to expel the paint at high speed, obtaining a much wider span and a more fluid coat of paint. For a perfect finish and optimum exterior resistance.

### **FEATURES**

- Very fast drying.
- High covering power.
- Good adhesion.
- Does not contain lead.
- Light weather resistance.
- Leafing aluminium.

## **APPLICATIONS**

Very suitable for painting any type of surface, giving a highly decorative metallic aspect. Very suitable for artworks.

- Graffiti Decoration. Fine arts Retouches for metallic components.
- DIY Plastics

Paint with low exterior resistance and low resistance to abrasion, which leads to a loss of the metallic appearance. Do not apply coats of varnish or other paints due to the leafing aluminium, which migrates to the surface.

# INSTRUCTIONS FOR USE


- Shake the aerosol well before using, approximately for one minute after hearing the sound of the mixer.
- Apply to clean, dry surfaces. On rusty metallic surfaces remove rust with a wire brush and prepare an anti-rust primer if considered necessary. Apply an anchor layer on plastics and polyesters.
- For best results apply in thin layers. Three thin layers are always better than one thick one, and may be repainted within fifteen minutes with the same paint.
- Turn the aerosol upside down to clean out the valve after use.
   If te nozzle becomes blocked replace it with a new one.
- Never apply to equipment that is plugged in and use in well ventilated areas.
- Request safety datasheets.

## PHYSICAL PROPERTIES

Type of liant:	Acrylic resin
Color:	Glossy paint
Dry to the touch (ASTM D-1640 ISO 1517):	10'
Completely dry(ASTM D-1640 ISO 1517):	30'
Thickness of dry layer (ASTM D-823 ISO 2808):	25 micras/layer (2 pasadas)
Adherence (ASTM D-3359 ISO 2409):	3 B
Theorical yield (continuous painting):	8,5 m <sup>2</sup> for 750 ml
Thinner:	Aromatic mixt
Product life:	(Well Stored) >5 years
Condition for application:	Minimum room temperature 8°C
	Surface temperature 5°C a 50°C
	Max humidity 85% R.H.P
Heat resistance of paint:	150°C
Repainted:	After 15'

<sup>\*</sup> All of the adherence tests have been carried out on iron plates

## **APPEARANCE**



LID
 Protects the valve and the nozzle.

LABEL CAP SYSTEM

65 mm























## **PACKAGING**

High pressure. Nominal capacity: 750 ml. Heat resistanve of packaging:  $<50^{\circ}$ C Propellant: GLP - HC C<sub>3</sub>-C<sub>4</sub>

Box (6 units) 200 X 340 X 140 mm.



