EPS PRIMER (STYROFOAM). Prepares and primes surfaces to be painted.
400 ml, 11.8 Oz, 334 g.

GENERAL DESCRIPTION

Grey acrylic primer that brings to expanded polystyrene surfaces a protection that allows post-painted with solvent based paints.

FEATURES

- Very fast drying.
- Easy to apply and recoat.
- Doesn't content lead.
- Perfect adhesion.
- Good coverage and filling capability.

APPLICATIONS

Indicated, as a primer layer to protect the expanded polystyrene in:

- Modeling   - Crafts   - Layouts   - Architectural Studies

INSTRUCTIONS FOR USE

- Before using, shake the aerosol vigorously for approximately one minute after the noise of the mixer starts. Paint with the container upright. Apply quick and fine layers at a distance of about 20 cm past.
- To obtain a perfect protection of the expanded polystyrene, it is important to cover accurately the whole surface, preventing unpainted pores or spaces.
We recommend applying a minimum of 5 thin layers, leaving 5-10 minute drying intervals between each layer.
- Once dry for 30 min apply any type of paint, hence avoiding any damage to the polystyrene.
- Don't spray on plugged-in equipment and use it only in well ventilated areas.
- Ask for MSDS.

PHYSICAL PROPERTIES

Binder:	Acrylic
Color:	Grey R.7001
Dry to touch (ASTM D-1640 ISO 1517):	10'
Total drying (ASTM D-1640 ISO 1517):	30'
Dryfilm thickness (ASTM D-823 ISO 2808):	10-15 µ/layer (2pasadas)
Adherence (ASTM D-3359 ISO 2409):	n/a
Theorical yield (pintado en continuo):	2 m²
Thinner:	Alcohol
Product life:	(Well Stored) 5 years
Recoating:	After 10'
Heat resistance:	n/a
Condition for application:	Tº min 8ºC
	Tº surface 5ºC-50ºC
	Humidity max. 85% R.H.P

*The adhesion tests were done on PP (EPDM modified). Last revi ew's date: 2/01/2017.

CAUTION

APPARENCE

LID
Protects the valve and the nozzle.

DONUT
Indicates the paint color.

200 mm.

65 mm.

EPS PRIMER (STYROFOAM)
CAN BE REPAINTED WITH ANY PAINT TYPE

LABEL

COD. BARRAS/BAR CODE

EX014PR0914 EPS Primer

CAP SISTEM

Pocket Cap
Medio - Medium

PACKAGING

Nominal capacity: 400 ml.
Heat resistanve of packaging: <50ºC
Propellant: GLP — HC C_3-C_4

Box (6 units)
205 X 140 X 200 mm.

Management System
ISO 9001:2008
ISO 14001:2004

Company certified according to quality standard
ISO 9001:2000
ISO 14001:2004

Made in Europe.